



SGS U.S. Testing Company Inc.

291 Fairfield Avenue • Fairfield, NJ 07004 • Tel: 973-575-5252 • Fax: 973-575-8271

CLIENT: Microgen Inc.
33 Clinton Road
Suite 102
West Caldwell, NJ 07006

Test Report No:	166639	Date:	April 2, 2002
-----------------	--------	-------	---------------

The following samples were submitted by the client as: Public Places RTU Disinfectant
Lot #9280113

DATE OF RECEIPT: March 22, 2002


TESTING PERIOD: March 29, 2002

AUTHORIZATION: Client Purchase Order #032202-1


TEST REQUESTED: The submitted sample was tested for Resistance to Chemicals in accordance with the procedure outlined in ASTM F925-97 and Client instructions.

TEST RESULTS: Continued on Page 2

PREPARED BY


Vincent J. Conforti, Supervisor
Engineering Physical Properties
rm

SIGNED FOR AND ON BEHALF OF
SGS U.S. TESTING COMPANY INC.


Frank Savino, Manager
Materials Evaluation

Page 1 of 2

This report is issued by SGS U.S. Testing Company Inc. under its General Conditions for Testing Services, as printed on reverse side. SGS U.S. Testing's responsibility under this report is limited to proven negligence and will in no case be more than the amount of the testing fees. Except by special arrangement, samples are not retained by SGS U.S. Testing for more than 30 days. The results shown on this test report refer only to the sample(s) tested unless otherwise stated, under the conditions agreed upon. Anyone relying on this report should understand all of the details of the engagement. Neither the name, seals, marks nor insignia of SGS U.S. Testing may be used in any advertising or promotional materials without the prior written approval of SGS U.S. Testing. The test report cannot be reproduced, except in full, without prior written permission of SGS U.S. Testing Company Inc.

Member of the SGS Group (Société Générale de Surveillance)



SGS U.S. Testing Company Inc.

Report No.: 166639
 Date: 4/02/01
 Page: 2 of 2

CLIENT: Microgen Inc.

RESULTS:

RESISTANCE TO CHEMICALS

<u>Specimen</u>	<u>Surface Dulling</u> 0 - 3	<u>Color Change</u> 0 - 3	<u>Surface Attack</u> 0 - 3
Steel AMS - 5045	0	0	0
Clad Aluminum	0	1	0
Cadmium Plate	0	0	0
Aluminum AMS-4037	0	1	0
Plexi Glass	0	0	0
Neoprene	1	0	1
HDPE	0	0	0
Polypropylene	0	0	0
Vinyl	1	0	0
Ceramic	0	0	0
PVC Plastic	0	0	0
Formica	0	0	0

Ratings

- 0 = No Change
- 1 = Slight Change
- 2 = Moderate Change
- 3 = Severe Change

End of Report